

FATIGUE PROPERTIES OF LOW CARBON STEEL STRENGTHENED BY STATIC OR DYNAMIC WORK HARDENING

UTRUJENOSTNE LASTNOSTI MALO OGLJIČNEGA JEKLA UTRJENEGA S STATIČNO IN DINAMIČNO DEFORMACIJO

JÁN MICHEL¹, J. HIDVÉGHY¹, I. MAMUZIĆ², M. BURSÁK¹

¹Department of Materials Science, Technical University, Kosice, Slovakia

²Metallurgical Faculty, University of Zagreb, Sisak, Croatia

Prejem rokopisa - received: 1998-12-06; sprejem za objavo - accepted for publication: 1998-12-14

The influence of strain rate on mechanical properties and fatigue resistance of low carbon steel (C content 0.04%) is shown. Experimental results are analyzed and relations derived describing the dependence of yield strength and ultimate tensile strength on prior strain rate in the range from 10^{-3} to 10^3 s⁻¹. The effect on fatigue resistance was analyzed, too. The impact hardened steel showed higher fatigue properties. Explanations are sought analyzing differences in microstructure and substructure of steel work hardened by static or impact strain.

Key words: low carbon steel, static and dynamic work hardening, static properties, fatigue properties

Določen je vpliv hitrosti hladne utrditve na mehanske lastnosti in odpornost proti utrujenosti za jeklo 0,04% C. Analizirani so eksperimentalni rezultati in razvite so enačbe, ki povezujejo mejo plastičnosti in natezno trdnost s hitrostjo predhodne hladne deformacije v razponu od 10^{-3} do 10^3 s⁻¹. Tudi vpliv na odpornost proti utrujenosti je analiziran. Udarno deformirano jeklo je pokazalo večje utrujenostne lastnosti. Razlaga se išče v razliki v mikrostrukturi in podstrukturi jekla, ki je bilo statično in dinamično deformacijsko utrjeno.

Ključne besede: malo ogljično jeklo, statična in dinamična deformacijska utrditev, statične lastnosti, utrujenostne lastnosti

1 INTRODUCTION

The loading rate influences the deformation process and changes the final properties of the metal. The strain resistance is growing with the increase of the strain rate. The loading rate changes also the plastic properties and the microstructure of the deformed material^{1,6,10,11,12}.

Several works reported on the dependence of fatigue resistance on the previous plastic deformation. In general, plastic deformation influences the quality of the surface and affects through it the fatigue process^{2,3}. Furtherly, plastic deformation changes the structure and the mechanical properties of the material, and changes the stress distribution in the product too^{3,4,5}. Generally, higher work hardening increases the fatigue limit, though it does not always improve other fatigue properties. The influence depends also on the amount of straining applied. For low amounts of deformation the influence is ambiguous^{1,3,6}.

The aim of the work was to show the importance of work hardening strain rate. The strain rate affects surface quality, microstructure, and stress distribution in the work hardened material, and consequently, also the fatigue resistance.

2 EXPERIMENTAL MATERIAL AND METHODS

The experiments were performed on low carbon steel (C 0.04%) rods with an initial diameter of 16 mm. The heat treatment consisted of the annealing at 950°C for 60

min and air cooling. It produced a polyhedral ferrite-pearlite microstructure, with a mean ferrite grain size of 0.031 mm and 5 vol.% of lamellar pearlite. The mechanical properties were as follows: $R_e = 210$ MPa, $R_m = 310$ MPa, $A_5 = 46\%$, $Z = 84\%$.

Rods of 12 mm in diameter were drawn with 10% reduction and two strain rates: $\epsilon_s = 2 \cdot 10^{-2}$ s⁻¹ on a universal tensile test machine ZDM10, and $\epsilon_d = 2 \cdot 10^2$ s⁻¹ on a drop weight impact test machine. The work hardened rods were then machined into test pieces and fatigue tested. The fatigue limit (σ_{CO}) was determined by rotational bending with the frequency of 24 Hz. Tensile test pieces were loaded with symmetric cycling $\sigma_a = \pm 150$ MPa at 16.6 Hz to 10^4 and $5 \cdot 10^4$ cycles. After fatigue loading the tensile testing was applied to evaluate the influence of cycling testing on mechanical properties. By tensile testing test pieces $d_0 = 4$ mm and $L_0 = 20$ mm, and different strain rates, from $\epsilon = 10^{-3}$ s⁻¹ to $\epsilon = 2,5 \cdot 10^3$ s⁻¹ were used.

3 RESULTS

The mechanical properties: yield strength R_e , ultimate tensile strength R_m , elongation A_5 and reduction of area Z are plotted in **Figure 1** in dependence on the work hardening strain rate. The strength grows with the growth of strain rate, and the growth is faster at higher dynamic strain rates ($\epsilon > 1$ s⁻¹). While the reduction of area Z did not show significant changes, the elongation A_5 decreased for high strain rates $\epsilon > 1$ s⁻¹.




Figure 1: Dependence of mechanical properties on work hardening strain rate for a low carbon steel

Slika 1: Vpliv hitrosti deformacijske utrditve na mehanske lastnosti maloogljčnega jekla

The aim of this contribution was also to find a mathematic description of the influence of strain rate on mechanical properties. Different formulas are proposed in references: The best fits were obtained with equations:

$$R_e = R_{e0} + A \log(\epsilon/\epsilon_0) \quad (1)$$

$$R_e = R_{e0} + K \cdot \log(\epsilon/\epsilon_0)^n \quad (2)$$

with:

R_e the strength (R_e , or R_m) at the strain rate ϵ ,
 R_{e0} the strengt for the static strain ϵ_0 ,
 A, K and n are constants of rate induced stress increase

For the tested steel the equations (1) and (2) into the form correspond with a correlation coefficient 0.95 into the form:




Figure 2: Woehler curves for a low carbon steel
 Slika 2: Wöhlerjeva krivulja za maloogljčeno jeklo

$$R_{ee} = 210 + 32.7 \log(\epsilon/\epsilon_0); R_{ee} = 210 + 19.8 \log(\epsilon/\epsilon_0)^{2.49} \quad (3)$$

$$R_{me} = 310 + 20.0 \log(\epsilon/\epsilon_0); R_{me} = 310 + 9.4 \log(\epsilon/\epsilon_0)^{2.1} \quad (4)$$

In the interval of tested strain rate from $\epsilon = 10^{-3} \text{ s}^{-1}$ to $\epsilon = 10^3 \text{ s}^{-1}$ the value of R_e and R_m can be predicted by these equations with small deviations.

The fatigue properties of the tested steel $\sigma_h - N$ (Woehler curve) in dependence on the previous static ($\epsilon_s = 2 \cdot 10^{-2} \text{ s}^{-1}$) and dynamic ($\epsilon_d = 2 \cdot 10^2 \text{ s}^{-1}$) work hardening are shown in Figure 2. As shown the 10% tensile plastic deformation increased the fatigue limit σ_{C0} , changed the slope of the Woehler curve and increased the scatter. The changes are influenced by the work hardening strain rate. The declined part of the Woehler's curve is typically expressed by a relation of the form $\log N = a + b \cdot \sigma$. The statistics of the influence are in Table 1.

Table 1: Fatigue statistics parameters of the tested steel

| Condition | a | b | σ_{C0} (MPa) | $\Delta\sigma_{C0}$ (MPa) | $\Delta\sigma_{C0}$ (%) |
|--|--------|---------|---------------------|---------------------------|-------------------------|
| initial | 6,935 | -0,0103 | ± 107 | - | - |
| 10% dynamic strain $\epsilon_s = 2 \cdot 10^{-2} \text{ s}^{-1}$ | 10,115 | -0,0313 | ± 116 | 9 | 8 |
| 10% static strain $\epsilon_d = 2 \cdot 10^2 \text{ s}^{-1}$ | 11,334 | -0,0384 | ± 126 | 19 | 15 |

The stress - strain curves in Figure 3 were obtained by tensile testing the material previously work hardened and then fatigue tested with symmetric tension/compression $\sigma_a = \pm 150 \text{ MPa}$ at 16.6 Hz to 10^4 and $5 \cdot 10^4$ cycles. The steel was softened (ΔR) by the long time cycling (to $N = 10^4$, and $5 \cdot 10^4$ cycles). The softening ΔR was measured at tensile testing to 0.5% and 3% strain. The dependence of softening ΔR on the number of cycles N applied is in Figure 4. It shows that ΔR depends on both, the number of cycles and the rate of previous work hardening. The saturation of softening is apparent at $5 \cdot 10^4$ cycles. To this limit are related the measured softening values given in Table 2.

Table 2: Softening by cycling of the tested work hardened steel

| Condition | $R_{0.5}$ (MPa) | R_3 (MPa) | $\Delta R_{0.5}$ (MPa) | ΔR_3 (MPa) | $\Delta R_{0.5}$ (%) | ΔR_3 (%) |
|-----------------------------------|-----------------|-------------|------------------------|--------------------|----------------------|------------------|
| 10% stat.strain N=0 | 365 | 400 | - | - | - | - |
| 10% stat.strain N= $5 \cdot 10^4$ | 270 | 323 | 95 | 77 | 26 | 19 |
| 10% dyn.strain N=0 | 303 | 372 | - | - | - | - |
| 10% dyn.strain N= $5 \cdot 10^4$ | 233 | 320 | 70 | 52 | 23 | 14 |

The cycling softening is stronger by the deformation level of 0.5%, while around the yield point, the higher is the strain the less distinct is the softening. UTS practically is not affected by cycling. The relative softening




Figure 3: Stress-strain curves in tension for a low carbon steel after static (3a) and dynamic (3b) work hardening by cycling at $\sigma_a = \pm 150$ MPa

Slika 3: Krivulje napetost-deformacija za nateg za maloogljikno jeklo po statični (3a) in dinamični (3b) deformacijski utrditvi s cikliranjem pri $\sigma_a = \pm 150$ MPa

ΔR is from 3% to 5% lesser in impact work hardened steel.

4 DISCUSSION

The results confirm the general rule - increasing the work hardening strain rate yield strength R_e and tensile strength R_m are increased also. The effect of strain rate is strongly dependent on steel microstructure. In equation (1) the strain rate intensity is expressed through the parameter A . If the values R_e and R_m represent the tested volume of the solid, then A can be calculated as function of R_e or R_m . Since values of $A_e = 31$ for R_e and $A_m = 15$ for R_m were obtained, it is than calculated:

$$A_e/R_e = 0.7 - 0.238 \cdot \log R_e \quad (5)$$

$$A_m/R_m = 0.237 - 0.076 \cdot \log R_m \quad (6)$$




Figure 4: Cycling softening ΔR influenced by static (S) and dynamic (D) work hardening. Low carbon steel

Slika 4: Ciklično mehčanje ΔR v odvisnosti od statične (S) in dinamične (D) deformacijske utrditve. Maloogljikno jeklo

Both equations describe the relative influence of strain rate on strength values. The higher the strength, the lower is the relative influence of strain rate.

Previous 10% strain increased fatigue limit and it caused also softening by cycling, all in good agreement with reported data. Our results show that these characteristics are also strain rate dependent.

The plastic deformation is not uniform all over the deformed body, which yields in bands between not deformed areas^{7,8}. The deformation is influenced by internal and external factors. To the external factors belong temperature, strain rate, and the applied amount of strain, while the internal factors are the properties of the work hardened material, strain process, and microstructure.

Therefore, the answer to the question, why is the fatigue limit σ_{C0} of the dynamic work hardened steel 7% higher than that of the static work hardened, is to be sought in the micro structure and substructure of the steel. As already reported^{7,9}, the dynamic plastic deformation is more uniform from the point of view of microstructure and substructure. This is shown also by the micrographs in **Figure 5 and 8**. The sub-micrographs show that after 10% of static strain cell pattern are well developed and the dislocation distribution in the cells is not uniform. After 10% of dynamic strain cell pattern are not completely developed, the cells are smaller and contain fewer dislocations. The mean cell size is for static strain 950 nm, and that for dynamic strain 615 nm. Cell pattern develop by greater deformation. By 25% of strain the




Figure 5: Substructure of a low carbon steel after static elongation 10% in tension

Slika 5: Podstruktura maloogljiknega jekla po 10% statičnem raztegu




Figure 6: Substructure of a low carbon steel after dynamic elongation 10% in tension

Slika 6: Podstruktura maloogljirnega jekla po dinamičnem 10% raztegu



Figure 8: Microstructure of a low carbon steel after dynamic elongation 10% in tension

Slika 8: Mikrostruktura maloogljirnega jekla po 10% dinamičnem raztegu



Figure 7: Microstructure of a low carbon steel after static elongation 10% in tension

Slika 7: Mikrostruktura maloogljirnega jekla po 10% statičnem raztegu




Figure 9: Microstructure of a low carbon steel after dynamic elongation 10% in tension and subsequent fatigue testing at $\sigma_a = \pm 150$ MPa for $N = 6 \cdot 10^4$ cycles

Slika 9: Mikrostruktura maloogljirnega jekla po dinamičnem 10% raztegu in po utrujenostnem obremenjevanju pri $\sigma_a = \pm 150$ MPa z $N = 6 \cdot 10^4$ ciklov

mean cell size decreased to 615 nm for static and 480 nm for dynamic strain and the distribution of dislocations in the cells is more uniform. The sliding bands are finer after dynamic plastic deformation (**Figure 7**), and cover a larger area (more grains), than after static deformation (**Figure 8**). In cycling work strengthened steel fatigue slide bands after dynamic strain are wider due to the more uniform plastic deformation, as shown in **Figure 9**. In steel work hardened by static strain new fatigue slide bands were not found. It is supposed that such bands developed inside the wide slide bands due to the previous static strain.

5 CONCLUSIONS

The aim of this paper was to analyze the influence of strain rate by work hardening on mechanical and fatigue properties of a low carbon steel.

Taking into account the results and discussion it is concluded:

- at tensile testing the increase of strain rate from static $\epsilon = 10^{-3} \text{ s}^{-1}$ to impact $\epsilon = 2 \cdot 10^2 \text{ s}^{-1}$ increased the yield point by 95%, UTS by 32%, elongation decreased by 26%, while the reduction of area did not change;
- the work hardening increased both, the short time as well as the conventional fatigue limits. The increase is work hardening strain rate dependent. A 10% static work hardening increased the fatigue limit by 8%, while by dynamic work hardening the increase was of 15%;
- the softening is observed in cycling work hardened steel. It increases grows with the number of cycles applied to a saturation limit. The value depends on the previous work hardening strain rate. Impact hardened steel is prone to softening;
- the influence of work hardening strain rate on fatigue properties is due to the increase of homogeneity of deformation distribution with the increase of strain rate; and
- the higher the strain rate at work hardening, the higher the beneficial effect on fatigue properties.

6 REFERENCES

- ¹ L. O. Sokolov, *Soprotivlenije metallov plastitseskoj deformácii*, Nauka, Moskva 1963
- ² V. Sedláček: *Unava hliníkových a titanových slitin*, SNTL, Praha, 1989
- ³ A. Puskár: *Vysokofrekvenčná unava materiálov*, DU, Zilina, 1997
- ⁴ K. Klesnil, P. Lukáš: *Unava kovových materiálu*, AKADEMIA Praha 1975
- ⁵ L. Kunz: *Mikrostrukturní aspekty kovu*, Thesis work, Brno, 1996
- ⁶ J. Michel, M. Bursák, I. Mamuzić: *Metallurgija*, 35 (1996) 2, 69-72
- ⁷ V. Sedláček: *Nehomogenita plasticke deformace*. In. "Deformácia a lom kovových sustav", DT CSVTS Kosice 1989
- ⁸ A. Puskár: *Mikroplastienost a porusenie kovových materiálov*, VEDA Bratislava, 1986
- ⁹ J. Michel: *Materiálove inžinierstvo*, 3 (1996) 2, 22
- ¹⁰ *Metals Handbook*, Vol 8, ASME, ISBN 0-87170-007-7, USA, 1985
- ¹¹ T. Kvacaj, I. Pokorny: *Mathematical model of stress - strain curves*, *Metallurgija*, 4 (1995) 145-149
- ¹² T. Kvacaj: *Tepelne deformacny rezim v priebehu prvej fázy riadeneho valcovania*, *Hutnik* 2 (1985) 50-53